(19) World Intellectual Property Organization International Bureau



(43) International Publication Date 3 January 2002 (03.01.2002)

PCT

(10) International Publication Number WO 02/00792 A1

(51) International Patent Classification⁷: C08L 75/04, C08F 283/00, C08G 18/10

(21) International Application Number: PCT/EP01/06190

(22) International Filing Date: 31 May 2001 (31.05.2001)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

00305342.8

23 June 2000 (23.06.2000) EP

- (71) Applicant (for all designated States except US): NATIONAL STARCH AND CHEMICAL INVESTMENT HOLDING CORPORATION [US/US]; 3411 Silverside Road, Wilmington, DE 19850 (US).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): FAUST, Hans, Uwe [DE/DE]; Eckener Strasse 4, 52078 Aachen Brand (DE). McLENNAN, Alistair, John [GB/NL]; c/o Vinamul B.V., POB 250, NL-6190 AG Beek (NL). SCHOFIELD, Kevin [GB/GB]; 5 St. Wilfrid's Drive, Grappenhall, Warrington, Cheshire WA4 2SH (GB).

- (74) Agent: WIESENHAAN, Herman; Looërmark 1, NL-7437 SH Bathmen (NL).
- (81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.
- (84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

Published:

with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: A POLYMER DISPERSION COMPRISING PARTICLES OF POLYURETHANE AND A COPOLYMER OR TER-POLYMER PRODUCED BY EMULSION POLYMERISATION OF OLEFINICALLY UNSATURATED MONOMERS

(57) Abstract: A polymer dispersion comprising an aqueous, continuous phase and dispersed particles of polyurethane, which is based on organic, non-aromatic isocyanates with a functionality of at least 2, said polyurethane having a high degree of crystallinity and whose crystalline phase has a melting point between 25 and 70 °C, and a copolymer and/or terpolymer having a T_g (glass transition temperature) between -20 and +50 °C obtainable by emulsion polymerization of ethylenically unsaturated monomeric materials containing only C, H, O and/or N atoms, which monomeric materials comprise from 0.5 to 15 percent on the total of monomeric materials of monomers containing at least one nitrile group, in a weight ratio between 50:50 and 10:90 (polyurethane to emulsion polymer), in which the particles of the dispersion are in the form of multiphase particles comprising said polyurethane and said copolymer and/or terpolymer and which dispersion is obtainable by emulsion polymerisation of the monomeric materials in the presence of the polyurethane dispersion, said eventual polymer dispersion having a solids content of 30 to 70 %. The invention also comprises the use of these dispersions as an adhesive, especially for heat seal laminating, preferably for 3-D(imensional) Laminating. The dispersion is also useful as a size for glass fibres.

